Supplier - ARKEMA VPS 11

Fatty Ester Triglyceride

Typical Properties

| Appearance | Light Brown Fluid |
|---|-------------------|
| Color,Gardner | < 7 |
| Viscosity@40°C,cSt | 200 - 300 |
| Viscosity@100°C,cSt | 35 |
| Copper Corr+ | ≤ 1b |
| Sulfur Content (Active),%wt | > 10 (<1) |
| H ₂ S Test,Acetate Paper Color | < 3 |
| Specific Gravity | 0.950 |
| Average Weight,lbs/gal | 7.93 |
| Flash Point,°C | > 150 |
| Pour Point,°C | ≤ -10 |
| $P_B / P_D + +$ | 80 / 250 |
| Load Wear Index ⁺⁺ | 42 |
| 4 Ball Wear(IP239,40kg,1h),mm | 0.5 |
| Reichert Test(300N Load),mm ² | 1.2 |
| Std Packaging (NW / GW, Kg) | 207.0 / 190.0 |

Product Description

VPS 11 is a light brown liquid with very slight odor and no chlorinated impurities. It is a lubricity- enhancing agent for industrial and metal working formulations, which also provides anti-wear and extreme pressure properties. It does not corrode copper alloys.

VPS 11 is recommended for the formulation of metal working fluids especially when working with copper and its alloys. Its EPS properties are enhanced when combined with Arkema Inc.'s **TPS** products (**TPS 20** is particularly recommended).

Print date: 13-09-25