

Supplier - SMART OIL

Smart HMPE 9310*High Mwt. Polyester Ester**High Molecular Wt Polymeric Ester***Typical Properties**

| | |
|---|--------------------|
| Appearance | Clear Amber Liquid |
| Specific Gravity@25°C | 0.900-1.000 |
| Viscosity@40°C, cSt | 180 - 230 |
| Acid Value, mgKOH/g | < 8 |
| Flash Point C.O.C., °C | > 200 |
| Viscosity Index | > 140 |
| Mineral Oil Content | Nil |
| 5%ADDITIVE++95%SN150 PB/PD,kg+ | 44/100 |
| 5%ADDITIVE+5%SMART BASE 2517+90%SN150 PB/PD,kg+ | 76/315 |

*4 Ball Wear Test; 5% additive in SN150, Server Motor Speeds reach 1500rpm (P_B) and 1760rpm (P_D) in 0.03sec.

Product Description

SMART HMPE 9310 is a clear amber, high molecular weight polymeric ester that contains no sulfur, chlorine and phosphorous. Due to its unique molecular structure and high affinity characteristics, it can adhere tightly to the metal surfaces even at elevated temperatures, which performs outstanding anti-frictional and anti-wear properties of lubricants. It can be used in several operations like oil-based formulations, soluble oils and semi-synthetic systems.

SMART HMPE 9310 has a high degree of saturation that can prevent contamination at contact points of tools and metal surfaces from oxidation.

SMART HMPE 9310 has high temperature stability and hydrolytic stability, which can extend coolant life even at tough processing.

SMART HMPE 9310 can replace sulfur, chlorine and phosphorous containing additives with similar performance. Moreover, it can avoid the reduction of product shininess due to the otherwise chemical reaction of the extreme additive with the metals during machining.

SMART HMPE 9310 possesses high viscosity index and good shear stability; which can maintain the corresponding functions of lubrication, anti-wear and extreme pressure at elevated temperatures at contact points during machining.

SMART HMPE 9310 is an ash-less additive and has no residue during high temperature operations. It exhibits no corrosion to non-ferrous metals and is suitable for cutting, drawing, and stamping operations on aluminum alloys.

Applications

Threading / Tapping / Cold Head (Cut Side Only)
Drawing
Automatic Screw Machines / Stamping

Suggested Treat Rates, %wt

3 - 15
5 - 15
2 - 5

Print date: 13-06-26

Disclaimer: Information provided by this website and product page including specifications, applications and formulations are based on tests and data supplied by Smart Oil companies, manufacturers or any of our collaborated companies or suppliers, which are believed to be correct and reliable at the time of writing and data update. However, Smart Oil companies, manufacturers or any of our collaborated companies or suppliers make no warranty or responsibility, express or implied, of any kind regarding products, performance, formulations or applications, as operation conditions and application environments are beyond our control, or products will be modified by action of manufacturers or due to change in market environments. Users are herewith expressly requested to conduct test to determine the suitability of our products or product information before use. Furthermore, we regret that we cannot be responsible for informing customers any changes in specifications, formulations, or other technical contents on this website and product page. Also, We hereby state that all product trademarks other than Smart Oil, including trademarks from our , suppliers are the trademarks belong to the respective companies, or from their sources.